


# Ludlow Tape® M-Tak® 7430L

## **Polyester Supported Double-Coated Tape**



Carrier: Polyester Film

Synthetic Rubber (HM805) Adhesive:

54# SC Kraft with Finger-Lift Edge™ Liner:

**Product Constructions Available** Number TW TL AW 7430L 1.75" 2200' 1.5"

#### **Applications**

- Lightweight corrugated mailer sealing
- Seals corrugate for expedited packaging
- SBS chipboard packaging seals
- Point-of-sale displays

#### **Benefits Features**

| Synthetic Rubber Adhesive | <ul> <li>High adhesion for a secure permanent<br/>bond to plastics, papers and mailers</li> <li>Strong initial tack</li> </ul> |
|---------------------------|--|
| PET Film Carrier          | <ul><li>Provides support and structure for added stability</li><li>Conformable</li></ul>                                       |
| Finger-lift Edge Liner    | Easy to start, easy to use   |

### **Typical Test Values**

|                                | Standard UOM  | Metric UOM   | Test Method  |
|--------------------------------|---------------|--------------|--------------|
| Tape Thickness (w/o liner)     | 5.9 mils      | 0.150 mm     | PSTC 133     |
| Liner Thickness                | 3.2 mils      | 0.081 mm     | PSTC 133     |
| Overall Thickness              | 9.1 mils      | 0.231 mm     | PSTC 133     |
| Adhesion to Steel (Air Side)   | 150 oz/in     | 16.41 N/cm   | PSTC 101 Mod |
| Adhesion to Steel (Liner Side) | 135 oz/in     | 14.77 N/cm   | PSTC 101 Mod |
| Application Temperature Range  | 45 to 120 °F  | 7 to 49 °C   |              |
| Operating Temperature Range    | -20 to 170 °F | -29 to 77 °C |              |

Recommended Storage Conditions: 60-80 °F at 40-60% RH Standard Shelf Life (at 25 °C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility

