


GTW-492

Double-Coated Foam Glazing Tape



Liner:	4 mil Blue PP
Liner Side Adhesive:	Acrylic (I636)
Backing/Carrier:	1/8" 4lb Closed-Cell, Crosslinked White (or Black) PE Foam
Air Side Adhesive:	Acrylic (I636)
Specifications:	AAMA 810.1-16 for glazing.

Note: Same product is also available on Black color foam as GTB-492

Applications

- Seal window glass onto wood, aluminum, or plastic frames
- Provides cushioning to absorb vibration and shock
- Seals against air, moisture, light, and dust
- Thermal insulating and sound deadening

Features

Benefits

<ul style="list-style-type: none"> • Acrylic Adhesive • Foam Carrier • PE Film Liner 	<ul style="list-style-type: none"> • Excellent quick stick • Moderate shear strength • Good UV resistance • Conformable • Minimal moisture absorption • Lends itself to die-cutting and kiss cuts
---	---

Typical Test Values

	Standard UOM		Metric UOM		Test Method
Overall Thickness (w/liner)	133.0	mils	3.378	mm	PSTC 133
Air-Side Adhesive Thickness	2.0	mils	0.051	mm	PSTC 133
Carrier Thickness	125.0	mils	3.175	mm	PSTC 133
Liner Side Adhesive Thickness	2.0	mils	0.051	mm	PSTC 133
Liner Thickness	4.0	mils	0.102	mm	PSTC 133
Adhesion to Steel (Air Side)	N/A*				PSTC 101 Mod
Shear Strength	>7 Days				PSTC 107 Mod
Laminating Temperature	68 to 100 °F		20 to 38 °C		
Service Temperature	-30 to 220 °F		-34 to 104 °C		

*Adhesive peel strength supercedes cohesive strength of the foam carrier.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To Berry Global's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which Berry Global assumes any legal responsibility.