


## Shadowlastic® Extreme - Window & Door Flashing Tape



**Backing:** Woven Polyethylene (Printed)

**Adhesive:** Butyl Rubber

**Liner:** Kraft Paper Liner

**Colors:** Black (w/White Print)

**Specifications:** AAMA 711-13, ASTM E2112  
15 Year Limited Warranty

**Standard Sizes:** 4" x 75Ft, 6" x 75Ft, 9" x 75Ft

### Applications

- Window and door installations
- Corner board abutments
- Side-wall sheathing seams
- Deck-to-wall joints
- Sealing other detail areas against water and air penetration

### Features

- Woven Polyethylene Backing
- Butyl Rubber Adhesive
- Paper Release Liner

### Benefits

- Conformable and durable
- Excellent air and moisture barrier properties
- Suitable for up to 3 years outdoor UV exposure
- Provides permanent weather-tight seal on most clean, dry building surfaces
- Excellent cold temperature adhesion
- Compatible with sealants and caulking
- Self-healing after puncture
- Used properly, can contribute toward requirements for EA Credit 1 (Optimize Energy Performance) under LEED®
- Easy to remove

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	14.5 mils	0.368 mm	ASTM D-1000
<b>Adhesion to Steel</b>	63 oz/in	6.89 N/cm	ASTM D903-93
<b>Adhesion to Plywood</b>	53 oz/in	5.80 N/cm	ASTM D903-93
<b>Adhesion to OSB</b>	30 oz/in	3.28 N/cm	ASTM D903-93
<b>Adhesion to PVC</b>	70 oz/in	7.66 N/cm	ASTM D903-93
<b>Adhesion to Housewrap</b>	50 oz/in	5.47 N/cm	ASTM D903-93
<b>Tensile Strength</b>	59 lb/in	103.33 N/cm	ASTM D412-97
<b>Installation Temperature</b>	10 to 180 °F	-12 to 82 °C	
<b>Operating Temperature</b>	-30 to 200 °F	-34 to 93 °C	

Recommended Storage Conditions: 60-80 °F at 40-60% RH

Standard Shelf Life (at 25 °C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.