


## PE Vapor Barrier Sealing Tape



**Backing:** Low Permeability PE Film

**Adhesive:** Acrylic

**Liner:** N/A

**Colors:** Red

**Standard Sizes:** 96mm x 55m

### Applications

- Seaming vapor barrier films and underlayment materials including 10, 15, and 20 mil films
- Splicing and seaming heavy-weight materials subjected to high abrasion and stress
- Concrete underlayment applications including patch, repair, and sealing penetrations coming through the slab
- Polyethylene splicing and patching

### Features

- Polyethylene Film Backing
- Acrylic Adhesive

### Benefits

- Tough and durable
- Exceptional vapor barrier properties
- Conformable
- Aggressive bond to polyethylene and other vapor barrier materials
- Moisture-resistant, resists mold growth
- Excellent all-temperature performance

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	6.0 mils	0.152 mm	ASTM D-1000
<b>Adhesion to Steel</b>	120 oz/in	13.13 N/cm	PSTC-101
<b>Tensile Strength</b>	13.6 lb/in	23.82 N/cm	ASTM D-1000
<b>Elongation</b>	900%		
<b>Application Temperature</b>	0 to 175 °F	-17 to 80 °C	
<b>Operating Temperature</b>	-22 to 212 °F	-30 to 100 °C	
<b>Permeance</b>	0.03 Perms		ASTM F1249

Recommended Storage Conditions: 60-80 °F at 40-60% RH

Standard Shelf Life (at 25 °C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.