


POLYKEN® 784SW

Premium High Temperature Splicing Tape



Backing: Release Treated PET Film

Adhesive: Silicone

Colors: Blue

Specifications: N/A

Standard Sizes: 2" x 72Yd, 3" x 72Yd

Applications

- Splicing low-surface energy materials
- Splicing coated or uncoated papers or corrugate
- Tape splicing/manufacturing
- Foil splicing

Features

Benefits

- | | |
|--|--|
| <ul style="list-style-type: none"> • Silicone Release-Treated PET Backing • Silicone Adhesive • Self Wound Construction | <ul style="list-style-type: none"> • Thin, low-profile film • Excellent tensile strength and durability • Blue for high visibility • Outstanding adhesion to low-energy substrates • Excellent shear strength for improved splice bond • Performs well in extremely high temperatures • Releases cleanly from adhesives and coatings • Easy to use |
|--|--|

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness	4.0 mils	0.102 mm	ASTM D-1000
Adhesion to Steel	50 oz/in	5.47 N/cm	PSTC-101
Tensile Strength	50 lb/in	87.56 N/cm	ASTM D-1000
Max Performance Temp	400 °F	204 °C	
Elongation	125%		

Note: Not recommend for wrapping rollers on slitting or coating equipment as process may generate unwanted static.

Recommended Storage Conditions: 60-80 °F at 40-60% RH

Standard Shelf Life (at 25 °C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.