


8275-92

UV Protek™ Outdoor Grade Surface Protection Tape



Backing: Exterior-Grade Aliphatic Polyurethane

Adhesive: Regenerative UV Acrylic (A227)

Liner: 94# Kraft Paper

Colors: Clear Specifications: N/A

Size Options: Incremental sizes 1/4" - 48" x 108Ft

Applications

 Surface protection on high-wear surfaces prone to chipping, scratching, or weathering

Protects outdoor plastics and teak furniture

 Long-term protection for marine and other outdoor equipment

• Leading edge protection for turbine blades

Features Benefits

| • | Polyurethane Film Backing | Provides UV protection for outdoor use | |
|---|---------------------------|--|--|
| | | • | Abrasion resistant |
| | | • | Excellent aging characteristics, non-yellowing |
| | | • | Transparent to allow for visual inspection |
| • | Regenerative UV Acrylic | • | Strong permanent bond |
| | | • | Removes clean from most surfaces |
| | | • | Will not lift, stain, or dry out |
| • | Kraft Paper Release Liner | • | Smooth clean release - easy to use |
| | | • | Die cuttable |

Typical Test Values

| | Standard UOM | Metric UOM | Test Method |
|-------------------------------|-------------------------|-------------------------|-------------|
| Total Thickness | 7.5 mils | 0.191 mm | PSTC-133 |
| Substrate Thickness | 6.0 mils | 0.152 mm | PSTC-133 |
| Adhesion to Steel (Initial) | 35 oz/in | 3.83 N/cm | ASTM D-3330 |
| Adhesion to Steel (@ 20 mins) | 45 oz/in | 4.92 N/cm | ASTM D-3330 |
| Tensile Strength | 50 lb/in | 87.56 N/cm | ASTM D-3759 |
| Puncture Resistance | 25 lbs | 11.34 kg | ASTM D-1000 |
| Elongation | 500% | | |
| Weight | 6.40 oz/yd ² | 217.00 g/m ² | |
| Abrasion/Wear Index | 0 | | ASTM D-4060 |
| Application Temperature | 50 to 120 °F | 10 to 49 °C | |
| Operating Temperature | -10 to 250 °F | -23 to 121 °C | |

Recommended Storage Conditions: 40-60% Humidity, 60 - 80 $^{\circ}$ F Standard Shelf Life (at 25 $^{\circ}$ C): 12 months from shipment date

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To BERRY GLOBAL'S knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY GLOBAL assumes any legal responsibility.

