



Polypropylene Surface Protection Tape

| Backing | Backing: | Embossed Polypropylene | |
|-----------------------------|---------------------|--|--|
| Adhesive | Adhesive: | Rubber (RF409) | |
| | Liner: | Self Wound or with 70# Kraft | |
| | Colors: | Clear, Tinted Red | |
| Single Coated Self Wound | Specifications: N/A | | |
| | Size Options: | Incremental sizes 1/4in - 58in x 108Ft | |

| Applications | | | | | | |
|--|---|---|--|--|--|--|
| Graphics protection for skis, snowboards, and outdoor equipment Screen and direct print (130 °C press temp) | | Protective mask for surfaces during lamination, molding, or machining where clean removal is critical | | | | |
| Features | | Benefits | | | | |
| Embossed Polypropylene Backing | • | Conformable and stretchy | | | | |
| | • | Transparent for easy inspection of surfaces | | | | |
| | • | Abrasion & moisture resistant | | | | |
| Rubber Based Adhesive | | Does not lift during molding or shaping | | | | |
| | • | Smooth, easy unwind | | | | |
| | • | Removes cleanly from most surfaces - no residue upon removal | | | | |
| | • | Excellent extreme temperature performance | | | | |

Typical Test Values

| | Standard UOM | | Metric UOM | | Test Method |
|-------------------------|---------------|-------|---------------|------|-------------|
| Total Thickness | 4.1 | mils | 0.104 | mm | PSTC-133 |
| Substrate Thickness | 3.5 | mils | 0.089 | mm | PSTC-133 |
| Adhesion to Steel | 19 | oz/in | 2.08 | N/cm | ASTM D-3330 |
| Tensile Strength | 14 | lb/in | 24.52 | N/cm | ASTM D-3759 |
| Elongation | 700% | | | | |
| Application Temperature | 50 to 120 °F | | 10 to 49 °C | | |
| Operating Temperature | -40 to 325 °F | | -40 to 163 °C | | |

Recommended Storage Conditions: 40-60% Humidity, 60 - 80 °F Standard Shelf Life (at 25 °C): 12 months from shipment date

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To BERRY GLOBAL'S knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY GLOBAL assumes any legal responsibility.

