
POLYKEN®

Seam & Seal™ Contractor Grade Sheathing Tape



Backing

Adhesive

Backing:

BOPP Film

Adhesive:

Acrylic

Liner:

N/A

Colors:

Red and White

Specifications: N/A

Topy VOC'S

Standard Sizes:

48mm x 50M, 72mm x 50M

Applications

- Sealing and seaming joints and overlaps in housewrap and interior/exterior vapor barrier
- Sealing exterior wall sheathing joints and extruded foam products
- Sealing window and door flanges or frames
- housewrap and interior/exterior vapor barriers Patching jobsite damage caused to wall Sealing exterior wall sheathing joints and sheathing and housewraps

Features Benefits

BOPP Backing	 Tough and durable 	
	 Hand tearable for ease of use 	
	 UV Resistant for outdoor installations up to 	
	180 days	
Acrylic Adhesive	 Aggressive bond - won't flag or lift 	
	 Mold and moisture resistant 	
	 Performs well in cold temperatures as well 	
	as high heat and high humidity conditions	
Low VOC Content	 Can contribute toward satisfying EQ Credit 4.1 	
	(Low Emitting Materials) under LEED®	

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness	3.2 mils	0.081 mm	ASTM D-1000
Adhesion to Steel	50 oz/in	5.47 N/cm	PSTC-101
Tensile Strength	32 lb/in	56.04 N/cm	ASTM D-1000
Application Temperature	-5 to 180 °F	-20 to 82 °C	
Operating Temperature	-40 to 212 °F	-40 to 100 °C	

Recommended Storage Conditions: 60-80 °F at 40-60% RH Standard Shelf Life (at 25 °C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

