
## **POLYKEN®**

# **727**Multi-Purpose PE Tape



**Backing:** Polyethylene Film

Adhesive: Rubber Liner: N/A

Colors: Orange, Black

Specifications: N/A

**Standard Sizes:** 48mm x 55m, 72mm x 55m

#### **Applications**

- Stucco and plaster masking
- General purpose outdoor masking
- Bunding, wrapping, and repairs
- General purpose abatement applications such as hanging and patching PE sheeting, securing waste disposal bags, and more

#### Features Benefits

| <ul> <li>Polyethylene Film Backing</li> </ul>     | <ul> <li>Conformable and flexible</li> </ul>                      |  |  |
|---|---|--|--|
|   | <ul> <li>Excellent durability and solvent resistance</li> </ul>   |  |  |
|   | <ul> <li>Withstands outdoor exposure and moisture</li> </ul>      |  |  |
| <ul> <li>Natural Rubber Based Adhesive</li> </ul> | <ul> <li>High tack for a secure bond</li> </ul>                   |  |  |
|   | <ul> <li>Repositionable and clean removal - no residue</li> </ul> |  |  |

### Typical Test Values

|                       | Standard UOM | Metric UOM | Test Method |
|-----------------------|--------------|------------|-------------|
| Total Thickness       | 7.5 mils     | 0.191 mm   | ASTM D-1000 |
| Adhesion to Steel     | 50 oz/in     | 5.47 N/cm  | PSTC-101    |
| Adhesion to Backing   | 25 oz/in     | 2.74 N/cm  | PSTC-101    |
| Tensile Strength      | 25 lb/in     | 43.78 N/cm | ASTM D-1000 |
| Operating Temperature | 40 to 180 °F | 4 to 82 °C |             |
| Elongation            | 70%          |            |             |

Recommended Storage Conditions:  $32-90 \, ^{\circ}\text{F}$  at 50% RH  $\pm \, 2\%$  Standard Shelf Life (at 25  $^{\circ}\text{C}$ ): 24 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.

