


GTW-192

Double-Coated Foam Glazing Tape



Liner: 4 mil Blue PP

Liner Side Adhesive: Acrylic (1636)

Backing/Carrier: 1/32" 6lb Closed-Cell, Crosslinked White (or

Black) PE Foam

Air Side Adhesive: Acrylic (1636)

Specifications: AAMA 810.1-16 for expanded cellular glazing

tape

Note: Same product is also available on Black color foam as GTB-192

Applications

- Seal window glass onto wood, aluminum, or plastic frames
- · Seals against air, moisture, light, and dust
- Provides cushioning to absorb vibration and shock
- Thermal insulating and sound deadening

Features Benefits

| Acrylic Adhesive | Excellent quick stick |
|------------------|---|
| | Moderate shear strength |
| | Good UV resistance |
| Foam Carrier | Conformable |
| | Minimal moisture absorption |
| PE Film Liner | Lends itself to die-cutting and kiss cuts |

Typical Test Values

| | Standard UOM | Metric UOM | Test Method |
|-------------------------------|---------------|---------------|--------------|
| Overall Thickness (w/liner) | 39.25 mils | 0.997 mm | PSTC 133 |
| Air-Side Adhesive Thickness | 2.0 mils | 0.051 mm | PSTC 133 |
| Carrier Thickness | 31.25 mils | 0.794 mm | PSTC 133 |
| Liner Side Adhesive Thickness | 2.0 mils | 0.051 mm | PSTC 133 |
| Liner Thickness | 4.0 mils | 0.102 mm | PSTC 133 |
| Adhesion to Steel (Air Side) | N/A* | | PSTC 101 Mod |
| Shear Strength | >7 Days | | PSTC 107 Mod |
| Laminating Temperature | 68 to 100 °F | 20 to 38 °C | |
| Service Temperature | -30 to 220 °F | -34 to 104 °C | |

^{*}Adhesive peel strength supercedes cohesive strength of the foam carrier.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To Berry Global's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation forwhich Berry Global assumes any legal responsibility.

