


# 3574A

# **Single-Coated Foam Tape**



Backing: 1/16" white, crosslinked polyethylene

foam

Adhesive: Non-sensitizing medical grade acrylic

(M108)

Liner: 2 mil polyester film, silicone coated on

one side

### **Applications**

Electrodes: ECG, EKG, TENS

AED defibrillator pads

Medical device mounting

Transdermal delivery system

### **Benefits Features**

<ul> <li>Polyethylene Foam Backing</li> </ul>	<ul> <li>Soft and flexible for maximum patient comfort</li> </ul>		
	<ul> <li>Conformable and easily adapts to medical</li> </ul>		
	devices and body contours		
Acrylic Adhesive	<ul> <li>Strong adhesion to surfaces</li> </ul>		
	<ul> <li>Stable to EtO and gamma sterilization</li> </ul>		
Polyester Film Liner	<ul> <li>Excellent lay flat and dimensional stability</li> </ul>		
	Easily die-cut		

## Typical Test Values

	Standard	Standard UOM		UOM	Test Method
Total Thickness w/liner	66.5	mils	1.689	mm	PSTC 133
Adhesive Thickness	2.0	mils	0.051	mm	PSTC 133
Carrier Thickness	62.5	mils	1.588	mm	PSTC 133
Liner Thickness	2.0	mils	0.051	mm	PSTC 133
Adhesion to Steel	100	oz/in	10.94	N/cm	PSTC 101 Mod
Liner Release	60	g/in	0.23	N/cm	ASTM D-5375
	Р	roduc	t Safetv	•	

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be noncytoxic, non-sensitizing, and non-irritating.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility

