


## Single-Coated Foam Tape



- Backing:** 1/32" blue, crosslinked polyethylene foam
- Adhesive:** Non-sensitizing medical grade acrylic (M108)
- Liner:** 74lb bleached polycoated kraft, silicone treated on one side

### Applications

- Electrodes: ECG, EKG, TENS
- AED defibrillator pads
- Medical device mounting
- Transdermal delivery system

### Features

- Polyethylene Foam Backing
- Acrylic Adhesive
- 74lb Release Liner

### Benefits

- Soft and flexible for maximum patient comfort
- Conformable and easily adapts to medical devices and body contours
- Strong adhesion to surfaces
- Stable to EtO and gamma sterilization
- Easily die-cut into various shapes and sizes
- Good dimensional stability and lay flat

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness w/liner</b>	38.8 mils	0.986 mm	PSTC 133
<b>Adhesive Thickness</b>	2.0 mils	0.051 mm	PSTC 133
<b>Carrier Thickness</b>	31.2 mils	0.792 mm	PSTC 133
<b>Liner Thickness</b>	5.6 mils	0.142 mm	PSTC 133
<b>Adhesion to Steel</b>	90 oz/in	9.85 N/cm	PSTC 101 Mod
<b>Liner Release</b>	80 g/in	0.31 N/cm	ASTM D-5375

### Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-irritating, and non-sensitizing.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

**Recommended Storage Conditions:** 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.