

6405

Rubber Transfer Tape



General purpose bonding to foams and other . low-surface energy materials

Features	Benefits	
Rubber Adhesive	High peel strengthExcellent initial tackGood shear strength	
12pt Polycoated Kraft Liner	 Rigid liner facilitates processing and 	

Typical Test Values					
Standa	ard UOM	Metric U	OM		
5.	0 mils	0.127	mm		
11	0	0 007			

	Standard UOM	Metric UOM	Test Method	
Adhesive Thickness	5.0 mils	0.127 mm	PSTC 133	
Liner Thickness	11.3 mils	0.287 mm	PSTC 133	
Adhesion to Steel	185 oz/in	20.24 N/cm	PSTC 101 Mod - 1 mil PET	
Adhesion to Steel	330 oz/in	36.10 N/cm	PSTC 101 Mod - 2 mil Alu Foil	
Loop Tack	240 oz/in	26.26 N/cm	PSTC 16	
Shear Strength (at 72 °F)	7 Days		PSTC 107 Mod	
Laminating Temperature	68 to 100 °F	20 to 38 °C		
Service Temperature	30 to 150 °F	-1 to 66 °C		

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To Berry Global's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation forwhich Berry Global assumes any legal responsibility.

