


Medical Transfer Tape



Dual Liner: 2 mil PET Film Liner
Adhesive: Silicone (M132)

Applications

- Laminating and bonding to low-surface energy materials and silicone foams
- Ideal for use in high temperature and harsh environments

Features

- Silicone Adhesive
- PET Film Liner

Benefits

- High peel strength adhesive
- Exceptional high temperature performance
- Good bond to LSE substrates
- Conformable and good dimensional stability

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	2.0 mils	0.051 mm	PSTC 133
Liner Thickness	2.0 mils	0.051 mm	PSTC 133
Adhesion to Steel	43 oz/in	4.70 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Polypropylene	38 oz/in	4.16 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Shear Strength (at 72 °F)	>7 Days		PSTC 107 Mod
Loop Tack	22 oz/in	2.41 N/cm	PSTC 16
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	-100 to 500 °F	-73 to 260 °C	

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic and non-irritating.

In accordance with FDA cGMP requirements, Berry Global reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.