




4142U-74

Rubber Transfer Tape



Release Liner

Liner:

74# PCK

Adhesive

Adhesive:

Rubber (I924)

Specifications:

Tested to numerous Automotive Specs

Applications

- Bonding to a wide variety of foams, felt, cork, rubber, and sponge materials
- Splicing applications
- Weatherstripping
- General purpose bonding uses
- Gasket, insulation, light shielding, and sound damping uses

Features

Benefits

- Rubber Adhesive System
- 74# Polycoated Kraft Liner
- Offers exceptionally high tack and high peel
- Excellent shear strength
- Well-suited for general purpose bonding to medium and high energy substrates
- Designed for bonding to various foams, as well as rough and porous surfaces
- Exhibits moderate bond to LSE substrates
- Conformable and good dimensional stability
- Suitable for die-cutting and other slitting operations

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Overall Thickness (w/liner)	7.5 mils	0.191 mm	PSTC 133
Thickness (Adhesive)	2.0 mils	0.051 mm	PSTC 133
Liner Thickness	5.5 mils	0.140 mm	PSTC 133
Peel Adhesion	190 oz/in	20.79 N/cm	PSTC-101 Method C
Loop Tack Adhesion	199 oz/in	21.77 N/cm	PSTC 16 Method A
Backing Release	9.96 g/in		PSTC-101 Method D - Modified
Shear Strength (1" x 1" x 1 Kg)	> 7 days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

