


Transfer Adhesive



Release Liner

Adhesive:

Rubber (1911)

Liner:

60lb super-calendered, silicone release treated on both sides

Applications

Laminating paper, felt, sponge rubber, foam, and plastic

- Component assembly
- General mounting applications

Features

•	Superior adhesion to common substrates
	for assembly, laminating, and mounting

Benefits

60lb Release Liner

Rubber Adhesive

Easy to die-cut and convert

• Excellent quick stick

Typical Test Values

	J		
	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	5.3 mils	0.135 mm	PSTC 133
Adhesive Thickness	1.8 mils	0.046 mm	PSTC 133
Liner Thickness	3.5 mils	0.089 mm	PSTC 133
Adhesion to Steel	170 oz/in	18.60 N/cm	PSTC 101 Mod
Shear Strength	<24 hours		PSTC 107
Laminating Temperature	50 to 150 °F	10 to 65 °C	
Maximum Continuous Use	175 °F	79 °C	
Intermittent Use	200 °F	93 °C	

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To Berry Global's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation forwhich Berry Global assumes any legal responsibility.

