



Greenhouse Film – Lumisol Clear (AF Available) 180mu (EN13206)

UV Stability				UV Transmission		
Region	Location	Lifetime on Structure		Wavelength (nm) >300	Transmission (%) > 50	
< 100kLy	Northern Europe	5 seasons	•	2000	7 00	
101-130kLy	Central Europe	4 seasons	•			
131-160kLy	Southern Europe	3 seasons				

Thickness	um	100 4500	
	I PIII	ISO 4593	180 (+/-5%)
% stretch	%	EN ISO 527-3	500-600
Tension to break	MPa	EN ISO 527-3	15-25
Force to break	gms	ISO 7765-1 1988	700-900
Description	Units	Test Method	Value ¹
Transmission of visible light	%	ASTM D1003-13	88-92
% of scattered light	%	ASTM D1003-13	30-35
Reduction of heat loss	%	BS EN13206	80-85
	Tension to break Force to break Description Transmission of visible light of scattered light	Tension to break Force to break Description Transmission of visible light % of scattered light %	Tension to break Force to break Description Transmission of visible light of scattered light MPa EN ISO 527-3 gms ISO 7765-1 1988 Units Test Method ASTM D1003-13

¹ Specified film properties only apply to film tested prior to installation. Please refer to our warranty document for guidelines on proper installation of the film and conditions of use.

In the event of failure, evidence (via XRF analysis) of high levels of sulphur, chlorine or iron will invalidate the guarantee. Specifically, contamination above these levels is excluded:

Sulphur: 1000ppm Chlorine: 150ppm Iron: 50ppm